

ISSUE: 04/01/2024

# **TECHNICAL DATA SHEET – HPC 126 NU-BASE HB EPOXY FLOOR FINISH**

# **DESCRIPTION:**

Nu-Base HB Epoxy Floor Finish is a two-pack solvent free resin. For use in most industrial floors including concrete and wood and provides a decorative dustfree finish. Being odour free and non-tainting is ideal for use in food industry, dairies, and breweries.

# **ADVANTAGES:**

Nu-Base HB Epoxy Floor Finish, has excellent resistance against distilled water, dilute minerals, acids and alkalis. Aggregates can be incorporated for improved slip resistance and wearing properties.

# **USES: FeRFA Class Type 3**

Nu-Base HB Epoxy Floor Finish is suitable for us in garages, workshops, warehouses and general industrial usage.

### COLOUR:

Clear and a selected colour range.

# **COVERAGE RATE:**

3-4 m<sup>2</sup> / KG

# **DRYING TIMES**

Touch dry Overcoat Full Cure 6 hours @ 20°C. 24 hours. 7 days.

# POT LIFE: 20 minutes @ 20°C

VOLUME SOLIDS: 100 %

### PACK SIZE

Two component product, supplied in 5 & 10 KG units



# PREPARATION:

All surfaces to be coated should be clean, dry and free from oil and grease etc. Ideally the substrate should be shot-blasted, mechanically abraded or acid etched with all loose, flaking materials and any laitance removed.

# APPLICATION:

By brush/roller or airless spray.

#### **EQUIPMENT CARE:**

All equipment should be cleaned with Nu-Base Epoxy Thinners. Conventional thinners and brush cleaners are not effective.

# STORAGE:

Recommended storage is in a cool, dry place with temperatures between 10-15 °C, and in accordance with the Highly Flammable Liquids and Liquefied Petroleum Gases Regulations 1972.

# SHELF LIFE:

12 months (in original sealed container).

HEALTH & SAFETY: Refer to MSDS



Unit 7 Phoenix Road Wednesfield Wolverhampton WV11 3PX, UK

TEL: +44(0) 1902 450 950

Data provided on this TDS is based on the best of our knowledge and experience, is given in good faith and should only be regarded as recommendations. No guarantee should be inferred and customers are advised to carry out their own tests under local conditions.