

ISSUE: 04/01/2025

# **TECHNICAL DATA SHEET – HPC 147 NU-BASE HYDROSEAL**

# **DESCRIPTION:**

Nu-Base Hydroseal is a two component epoxy resin surface damp-proof membrane. Designed to suppress the effect of residual moisture in concrete that already contains an integral D.P.M.

# **ADVANTAGES:**

Nu-Base Hydroseal enables earlier access onto the floor than would otherwise be available for the application of resin finishes and other floor coverings including carpets, tiles, vinyl and wood.

# **USES: FeRFA Class Type 3**

Easily applied by brush, roller or trowel. Can be applied on to substrates with hydrometer readings up to 97% R.H. Completely solvent free and low odour.

# COLOUR:

Clear

# **COVERAGE RATE:**

4 m<sup>2</sup> / KG @250 microns.

# **DRYING TIMES**

# Touch dry6 hours @ 20°C.Overcoat12 hours.Full Cure7 days.

# POT LIFE:

60 minutes @ 20ºC

#### Unit 7 Phoenix Road Wednesfield Wolverhampton WV11 3PX, UK

TEL: +44(0) 1902 450 950

# **VOLUME SOLIDS:**

100 %

# PACK SIZE

Two component product, supplied in 5 KG units.

# **PREPARATION:**

All surfaces should be clean, dry and free from oil and grease etc. Ideally the substrate should be shotblasted, scarified or scabbled first to provide a sound surface with a good mechanical key. All traces of concrete hardeners must be removed, and the surface must vacuumed to remove all traces of concrete dust. The area must be protected against further contamination prior to application.

# **APPLICATION:**

By brush/roller or hand trowel.

# **EQUIPMENT CARE:**

All equipment should be cleaned with epoxy thinners immediately after use.

# STORAGE:

Recommended storage is in a cool, dry place with temperatures between 10-15°C, and in accordance with the Highly Flammable Liquids and Liquefied Petroleum Gases Regulations 1972.

# SHELF LIFE:

12 months (in original sealed container).

# **HEALTH & SAFETY:**

Refer to MSDS



Data provided on this TDS is based on the best of our knowledge and experience, is given in good faith and should only be regarded as recommendations. No guarantee should be inferred and customers are advised to carry out their own tests under local conditions.