



TECHNICAL DATA SHEET – HPC 149 NU-BASE PITCH EPOXY FLOOR FINISH

DESCRIPTION:

Nu-Base Pitch Epoxy Floor Finish is a two pack solvent free resin, for use on most industrial floors including concrete and asphalt and provides a decorative dust-free finish.

ADVANTAGES:

Nu-Base Pitch Epoxy Floor Finish, has excellent resistance against distilled water, dilute minerals, acids and alkalis. Aggregates can be incorporated for improved slip resistance and wearing properties.

USES: FeRFA Class Type 3

Nu-Base Pitch Epoxy Floor Finish is suitable for use in cellars and related areas, sewage works, ramps and bridge decks (generally incorporating anti-slip aggregates) and walkways. Will cure at low temperatures down to 5°C.

COLOUR:

Black

COVERAGE RATE:

4 m² / KG @200 microns.

DRYING TIMES

Touch dry	6 hours @ 20°C.
Overcoat	12 hours.
Full Cure	7 days.

POT LIFE:

30 minutes @ 20°C

VOLUME SOLIDS:

100 %

PACK SIZE

Two component product, supplied in 5 KG units.

PREPARATION:

All surfaces to be coated should be clean, dry and free from oil and grease etc. Ideally the substrate should be shot-blasted, mechanically abraded or acid etched with all loose, flaking materials and any laitance removed.

APPLICATION:

By brush/roller or airless spray.

EQUIPMENT CARE:

All equipment should be cleaned with water immediately after use.

STORAGE:

Recommended storage is in a cool, dry place with temperatures between 10-15°C, and in accordance with the Highly Flammable Liquids and Liquefied Petroleum Gases Regulations 1972.

SHELF LIFE:

12 months (in original sealed container).

HEALTH & SAFETY:

Refer to MSDS